

HEAT TREATMENT RECOMMENDATION

Z-T15 PM[®]

STANDARD VACUUM



GRADE

Z-T15 PM[®]

METHOD

Standard Vacuum (4 Bar Minimum Quench Recommended)

RACKING

Parts should be placed in basket with adequate spacing to allow even heating and good exposure to quench gas. Long thin parts should be held in vertical position to maintain flatness/straightness.

HEATING

Use of staged preheating recommended:

- _ Ramp furnace to 1250±50°F and equalize temperature.
- _ Use convective heating if possible
- _ Ramp furnace to 1550±50°F and equalize temperature.
- _ Ramp furnace to 1950±50°F and equalize temperature.
- _ Advance to high heat

HARDENING

	for toughness	for wear resistance
High heat set point	2100 °F	2215 °F
Acceptable batching range	2080/2120 °F	2200/2230 °F
Soaking time in min.	10 - 25 min.	7 - 12 min

QUENCHING

- _ Back fill to positive pressure (minimum 4-6 bar ideal), and fan quench
- _ Cool at maximum possible rate until load temperature < 1300°F
- _ Continue cooling load to room temperature (<120°F)
- _ Parts should be tempered within 4 hours

TEMPERING

Select tempering temperature based on hardness specification:

	After 2100 °F	After 2215 °F
1020 °F	64-66	66-68
1040 °F	63-65	65-67
1060 °F	62-64	64-66
1100 °F	61-63	-

Optimum tempering range is 1020 to 1040 °F

TRIPLE TEMPER REQUIRED

1st temper	Heat parts to selected temperature, equalize and soak 2 hours. Cool parts completely to room temperature (<120°F)	Can use vacuum/inert gas or air (depending on finish); Use convective heating and fan cooling
2nd and 3rd temper	Repeat first temper cycle	-
Stress relieve	Heat parts to 950/975 °F, equalize and soak 1 hour	Stress relieve can be performed after hard finishing and/or EDM operations (vacuum methods preferred on finished tools)

TOOLING ALLOYS

Zapp Tooling Alloys Inc.
475 International Circle
Summerville, South Carolina 29483
Phone: 1 888 928 9927
Fax: 1 843 871 2157
ztasales@zapp.com

Zapp Tooling Alloys Inc.
1528 St. Paul Avenue
Gurnee, Illinois 60031
Phone: 1 888 928 9927
Fax: 1 843 871 2157
ztasales@zapp.com

Further information regarding our products and locations are available in our image brochure and under www.zapp.com

The illustrations, drawings, dimensional and weight data and other information included in these data sheets are intended only for the purposes of describing our products and represent non-binding average values. They do not constitute quality data, nor can they be used as the basis for any guarantee of quality or durability. The applications presented serve only as illustrations and can be construed neither as quality data nor as guarantee in relation to the suitability of the material. This cannot substitute for comprehensive consultation on the selection of our products and on their use in a specific application. The brochure is not subject to change control.

Last revision: February 2019